

Basis	<b>Flexible casting resin</b>
Resin	<b>GM 972 Comp. A (polyole)</b>
Hardener	<b>GM 972 Comp. B (Isocyanate)</b>
Colour	beige
Further hardeners	<b>PUR 11 Comp. B</b>

### Applications

- elastic component
- Vacuum casting parts
- Casting mould for gypsum
- Casting mould for plastic
- Casting mould for wax
- Casting mould for PU-foam
- fixtures

### Properties

- Shore A hardness 86
- well castable
- high strength
- cold flexible
- easily dyeable

### Processing data

Product		Mixture GM 972 / Comp. A+B	Resin GM 972 Comp. A (polyole)	Hardener GM 972 Comp. B (Isocyanate)
Colour		beige	white	yellow clear
<b>Mixing ratio</b>	<b>p. b. w.</b>		<b>100</b>	<b>45</b>
Viscosity at 25°C	mPas	-	1500 ± 500	150 ± 30
Density at 20°C	g / cm <sup>3</sup>	1,1 ± 0,02	1,03 ± 0,02	1,22 ± 0,02
Pot life 200 g / 20°C	min.	6 - 8	-	-
Curing time at RT	hrs.	3 - 5	-	-

### Physical data

Properties	Inspect. requirem.	Unit	Value
Tensile strength	EN ISO 527	MPa	11 ± 2
Tensile strength / test piece type 2	ISO 37	MPa	-
Tensile modulus / test piece type 2	ISO 37	MPa	-
Elongation at break / test piece type 2	ISO 37	%	-
Impact resistance (Charpy)	EN ISO 179	kJ/m <sup>2</sup>	-
Compressive strength	EN ISO 604	MPa	-
Heat resistance (Martens)	DIN 53458	°C	-
Shore hardness	DIN 53505	Shore A	86 ± 3
Coefficient of linear expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	-
Linear shrinkage	internal	%	-
Tear resistance / angle test piece	EN ISO 34-1	kN/m	50 ± 5
Tear resistance arch shaped test piece with incision 1 mm	DIN ISO 34-1	kN/m	-
Tear resistance arch shaped test piece without incision 1 mm	DIN ISO 34-1	kN/m	-
Elongation	EN ISO 527	%	600 ± 100
water absorption 35 - 40°C 63 d	internal	%	-

### Sales units (packages)

Packing size	B - Pack	GM 972 / Comp. A+B	Resin 9 x 0,600 kg / Hardener 9 x 0,270 kg = 7,830 kg
Units	Komp. A	GM 972 Comp. A (polyole)	5,000 kg
	Komp. B	GM 972 Comp. B (Isocyanate)	2,250 kg

## Processing instructions

Material- and working- temperature: between 18 - 25 °C.

Close containers after use.

Seal porous mould surfaces first (**ebalta** mould sealer).

For optimum mould releasing we recommend a special release agent (like T1-1), which can be applied easily with a brush or be sprayed. Releasing of the mould 2-3 times, evaporate for about 20 min. after each releasing.

Mixing ratio resin/hardener according to instructions.

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent

Both components can be easily mixed free from air bubbles in small quantities by hand with a stirring rod or in larger quantities with a spiral stirrer.

The processing in a vacuum is also possible.

For fast demoulding:

Material temperature: 25 – 30 °C

Moulding temperature: 70 - 80°C

Demoulding time: approx. 15 minutes (at 80°C moulding temperature)

## In General

The product is a Polyurethane system.

With the additive DT the casting resin GM 972 can also be used as a brushable and past-like surface resin.

We recommend 10-12 g additive DT per 1,000 kg.

When using GM 972 with a lower shore hardness we recommend the hardener PUR 11 (shore hardness: shore A 78±3).

## Storing

Storage at room temperature 18-25 °C.

Opened containers should be closed immediately after use and should be used up as soon as possible.

Shelf life is indicated on the labels.

## Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices!

## Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** UK Limited . B2 Langham Park, Trent Lane . Castle Donington . Derbyshire DE74 2UT  
t: +44 1332 814700 . f: +44 1332 814775 . e: info@**ebalta**.co.uk . w: www.**ebalta**.co.uk