## ebaboard 1204



Basis ebaboard 1204

Colour yellow Further colours black

# Applications

Pattern plates
 Foundry patterns
 Core boxes
 high abrasion resistance
 impact resistant
 dense surface
 good edge stability

### **Processing data**

Product		ebaboard 1204			
Colour		yellow			
Density at 20°C g / cm³		1,20 ± 0,02			

**Properties** 

# Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	120 ± 5
Flexural elongation at break	EN ISO 178	%	6,9 ± 0,5
Flexural modulus	EN ISO 178	MPa	2950 ± 300
Tensile strength	EN ISO 527-1	MPa	-
Impact resistance (Charpy)	EN ISO 179	kJ/m²	66 ± 9
Compressive strength	EN ISO 604	MPa	90 ± 5
Heat resistance (HDT)	DIN EN ISO 75 B	°C	87 ± 3
Shore hardness	DIN ISO 7619-1	Shore D	84 ± 3
coefficient of thermal expansion	internal test / Dilatometer	10 <sup>-6</sup> K <sup>-1</sup>	ca. 77
Abrasion Taber Abraser H 18 Application weight 500g / 500 Rotations	internal	mg	ca. 105

## Sales units (packages)

**ebaboard** 1204 1000 x 500 x 50 mm

1000 x 500 x 75 mm 1000 x 500 x 100 mm

Block material, ebablock 1204

dimensions variable

tooling resins . blocks . auxiliaries . silicones

as of: 06.11.2012 Revision: 3

#### ebaboard 1204



#### **Processing instructions**

Advices for machining of board material

- -Making even of milling support
- -Roughing of geometry
- -Removing of clamps, if possible over night
- -Clamping
- -Finishing

For bonding and repairing we recommend our adhesive yellow as well as our repair putty yellow.

The repair putty can also be used as fast adhesive and can be mixed individually with the adhesive following the indications of a mixing table in order to set up the pot-life.

For changes we recommend the casting compound yellow

#### In General

**ebaboard** material is available in specified sizes. The surface is machined on all sides. **ebaboard** is a synthetic, post-cured board material on polyurethane base. It has an even structure and plane parallel machined surfaces.

Advantages:

Dense structure
Good edge strength
Low tension
Good workability
Low dust development when milling

Dimension tolerances of 3 mm in length and width and 0,5 mm in thickness are possible.

### Safety measure

**ebaboard** material is a cured filled polyaddition product, no hazardous dusts when grinding.

According to regulations for hazardous goods **ebaboard** products don't have to be marked during transport and storage.

According to regulations for hazardous products all **ebaboard** products are not to be marked for transport and storage. Please follow safety advices!

#### **Waste Disposal**

Small quantities can be disposed as domestic waste. For big quantities, contact your local authorities, please.

In case of further questions please do not hesitate to contact our department for product safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

tooling resins	blocks	-	auxiliaries	•	silicones	

as of: 06.11.2012 Revision: 3 Page: 2