



Milling-parameter ebaboard 0780



$$vc = \frac{n \cdot \pi \cdot d}{1000} \quad [\text{m/min}]$$

$$fz = \frac{vf}{z \cdot n} \quad [\text{mm}]$$

$$n = \frac{vc \cdot 1000}{d \cdot \pi} \quad [1/\text{min}]$$

$$vf = n \cdot fz \cdot z \quad [\text{mm/min}]$$

Technical datas	Machining 1	Machining 2	Machining 3	Machining 4	Machining 5	Machining 6	Machining 7
Strategie		Profile roughing	Roughing Pocket	Roughing Residual material Z - constant	Finishing face milling	Finishing Z - constant	Engraving
Type of milling cutter	EMZ90 V22.042TH050 (1043249)	EBG T25.025AN140 (6121224)	DHCø12 INOX	EBG V12.012AN120-C (6128023)	EBG V10.010AN100-C (6130578)	EBG R08.008AP100-C (9148824)	Airline ball (1121894)
indexable inserts	VCGT 220530-ALM (1069759)	WPR 25 AS (9120404)	-	WPB 10 CF 10 (6128107)	WPB 10 CF 10 (6129238)	WPR 08 DN (6131629)	-
Cutting diameter [mm]	42	16	12	12	10	8	2
Number of tool cutting edges	3	2	4	2	2	2	2
Radius [mm]	3	3	0	2	1	4	1
Cutting speed vc [m/min]	600	500	340	500	450	380	100
Revolutions n [1/min]	4547	9947	9000	13262	14323	15120	15900
feed per tooth fz [mm]	0,5	0,4	0,15	0,3	0,15	0,2	0,1
Feed rate vf [mm/min]	6820	7957	5304	7957	4297	6050	3180
Axial depth of cut ap [mm]	5	2,5	10	2	0,5	0,2	0,3
Radial depth of cut ae [mm]	30	2,5	6	8	6	0,5	0

Determination of milling-parameters

machining of a 3-D Modell

